



## Alpha Maritex® Style 1000-2-PU

### TECHNICAL DATA

Base Fabric				Tolerance	Test Methods
Yarn	Warp	ET9	860 tex	± 5%	DIN 53830-3
	Weft	ET9	1.250 tex	± 5%	
Thread Count	Warp	6,0	1/cm	± 5%	DIN EN 1049-2
	Weft	4,0	1/cm	± 5%	
Weight		1.000	g/m <sup>2</sup>	± 5%	DIN EN 12127
Weave		Plain			ISO 9354
Temperature Resistance		550°C			

Coated Fabric				Tolerance	Test Methods
Coating	coated with silver-grey (with aluminium pigments) flame retardant PU on both sides to increase the fray-proofness and antislip-properties of the material				
Weight		1.200	g/m <sup>2</sup>	± 10%	DIN EN 12127
Thickness		1,5	mm	± 10%	DIN EN ISO 5084
Tensile Strength					DIN EN ISO 13934-1
	Warp	> 3.000	N/5cm		
	Weft	> 2.750	N/5cm		
Temperature Resistance		200°C			