



ENDLESS TAPES

Data - Sheet

AHMED & SONS Type		ARI 78	
Material		Aramide	
Surface		Plain	
Thickness		0.58 mm	
Lateral tape flexibility		medium	
Temperature resistance		up to 200 °C	
Wear resistance		very high	
Elongation at 150 N/cm		0.8 %	
Breaking strength		2350 N/cm	
Coefficient of friction		0,40μ	
		to paper	
		to garniture	
		0,20μ	
Tolerance		+ 1,0 % / - 0,0 %	
		length	
		+ 0,0mm / - 0,5mm	
		width	
		+ 0,05mm / - 0,02mm	
		thickness	
Recommended for		MARK 8	MARK 9
Cigarette and Filter production		KDF 2	GARANT
		PM5	SASIB

The information and recommendation contained herein represent the best information available to AHMED & SONS at the time of preparation. Modifications are possible without prior notice. The values stated are for information only. they do not guarantee a specific property.